

BODO Plastics Co.,Ltd.

TEST REPORT

SCOPE OF WORK

WPC Flooring

REPORT NUMBER

221028009SHF-009

TEST DATE(S)

2022-10-28 - 2022-11-22

ISSUE DATE

2022-11-22

PAGES


5

DOCUMENT CONTROL NUMBER

LFT-APAC-SHF-OP-10k(September 1, 2022)

© 2022 INTERTEK

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch



Test Report

Statement

- 1.This report is invalid without company's special seal for testing on the assigned page.
- 2.This report is invalid without an authorized person's signature.
- 3.This report is invalid if altered.
- 4.Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Don't copy this report in partial without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.
- 5.This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.
- 6.Except for the obligation, responsibility and liability (if any) for the appropriateness and professionalism of afore-mentioned testing itself within the scope and amount of the testing fee received, Intertek does not and will not accept any other obligation or liability.
- 7.If the Client has any questions about the test results, Intertek B&C should be informed within the storage period of the samples. The sample storage period ends 5 working days after the official report issue date. Samples of certification program are retained for the period required by the certification rules. The samples storage period shall be calculated according to the issue date of the original report in the case of quoting results and modifying reports.
- 8.Intertek B&C will service this report for the entire test record retention period. The test record retention period ends 6 years after this report original issue date. The test record retention period for certification program is 10 years. Test records and other pertinent project documentation will be retained for the entire test record retention period.
- 9.The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.



Test Report

Issue Date: 2022-11-22 Intertek Report No. 221028009SHF-009
Applicant: BODO Plastics Co.,Ltd.
Address: Economic Development Zone, Yi yuan County, Zibo City, Shandong Province
Attn: Jian Ma
Manufacturer: BODO Plastics Co.,Ltd.
Address: Economic Development Zone, Yi yuan County, Zibo City, Shandong Province
Test Type: Performance test, samples provided by the applicant.

Product Information

Product Name	WPC Flooring	Brand	BODO
Sample Description	Good Condition	Sample Amount	13pcs
		Received Date	2022-10-26
Sample ID	Model	Specification	
S221028009SHF.026	BTWF-001	1524mm*180mm*9.5mm	

Test Methods And Standards

Test Standard	ASTM D6007-14
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1.This report does not involve sampling. The report only reflects conformity of the tested items of the samples provided by the testing applicant. Representativeness and authenticity of the submitted samples are responsibilities of the testing applicant.

Report Authorized



 Name: Flora Fan Name: Aaron Cai
 Title: Reviewer Title: Project Engineer

Test Report

Issue Date: 2022-11-22

Intertek Report No. 221028009SHF-009

Test Items, Method and Results:

Test Item: Formaldehyde content test


Test Method: As per ASTM D6007-14 small scale chamber method, formaldehyde content was detected by UV-VIS spectrophotometer.

Test condition:

Chamber type:	0.225 m ³ stainless steel chamber
Climatic conditions:	25°C, 50% R.H.
Air exchange rate:	0.5 h ⁻¹
Loading factor:	0.43 m ² /m ³
Test result:	ND

Note:

1. ppm = parts of formaldehyde per million parts air
2. Detection limit = 0.02 ppm
3. ND = Not detected (less than the detection limit)
4. The sample was conditioned at 24±3 °C, 50±5% relative humidity for seven days before the testing.
5. Test location: Central Chemical Lab of Intertek Testing Services Shenzhen Ltd. Guangzhou Branch
Address: E701. No. 7-2. Caipin Road, Guangzhou Science City, GETDD Guangzhou, China 510663



Test Report

Issue Date: 2022-11-22

Intertek Report No. 221028009SHF-009

Appendix A: Sample Received Photo



Revision:

NO.	Date	Changes
221028009SHF-009	2022-11-22	First issue